

5cSt Pure Silicone Fluid

Low Viscosity PDMS Silicone Fluid (CAS # 63148-62-9)

PSF-5cSt Pure Silicone Fluid is a linear low viscosity 100% PDMS Silicone Oil or Polydimethylsiloxane (CAS # 63148-62-9) that has a viscosity of 5cSt (centistokes) @ 25°C. It does not contain additives or solvents.

Pure Silicone Fluid 5cSt is characterized by its low viscosity (close to water), low pour point, wide service temperature range, low V.T.C. (little viscosity change at both low and high temperatures), excellent lubricity, low surface tension (high spreadability), high dielectric strength, and high damping action (meets VV-D-1078 "Silicone as Damping Fluid"). It is the lowest viscosity that will not evaporate in an open system.

PSF-5cst is widely used as a heat transfer fluid and bath fluid due to its low viscosity and thermal properties.

5cStPure Silicone Fluid is inert to virtually all O-rings, gaskets, valves and seals. It is an excellent lubricant for plastic, rubber and foam surfaces.

Other uses include: Damping Fluid, Low Temperature Bath Fluid, Heat Transfer Fluid, Dielectric Fluid, Rubber and Plastic lubricant, O-Ring lubricant.

Specifications

Product code	5cSt
Chemical Name	Polydimethylsiloxane / PDMS
INCI/CTFA Name	Dimethicone
CAS #	63148-62-9
Appearance	Clear Liquid – Odorless & Tasteless
Viscosity Class	Low
Non-Flammable	Yes
Thermally Stable	Yes

Features

- Lowest viscosity that will not evaporate
- Excellent Lubrication
- Non-Flammable
- Low Pour Point
- Low Surface tension
- Low V.T.C (little viscosity change at both high and low temperatures)
- Chemically Inert
- High Compressibility
- High Damping Action...
- High Oxidation Resistance
- VOC exempt

Typical Product Data

Specific Gravity	Viscosity-Temp Coefficient	Flash Point	Pour Point	Refractive Index	Surface Tension	Vapor Pressure @ 25°C	Max volatility, % wt loss @ 150°C
0.918	0.54	135°C	-90°C	1.3970	19.7	1mmHg	90%

Thermal Properties

Boiling Point	Thermal Conductivity @ 50°C g cal/cm•sec• °C	Thermal Expansion cc/cc °C	Specific Heat cal/g/ °C
>200°C	0.00028	0.00109	0.390

Dielectric Properties

Volume Resistance @ 25°C	Dielectric constant 50Hz @ 25 °C	Dielectric strength volts/mil
1.0×10^{15}	2.60	375

**All types of Packaging available,
Including but not limited to...**

8oz. plastic dropper
1 pound "F" style
1 Quart "F" style
5 pound – double tight
5 pound – plastic pail
16 pound – plastic keg
55 gallon drum

For More Info, Contact:

ARtech Lubricants
18 Taylor Avenue
Bethel, CT 06801

Tel: (845) 858-8558

Fax: (845) 858-8338

Email: info@artechlubricants.com

Web: www.artechlubricants.com

